



Test results of ABS 6100

Description	Standard	Condition	Result	Unit
Tensile strength @Yield	ISO 527	Speed 5 mm/min Grip 115 mm	39.19	Mpa
Elongatin @ Break	ISO 527	Speed 5 mm/min Grip 115 mm	9.87	%
Tensile strength @ Break	ISO 527	Speed 5 mm/min Grip 115 mm	34.24	Mpa
Elongatin @ Yield	ISO 527	Speed 5 mm/min Grip 115 mm	3.92	%
Flexural Modulus	ASTM D790	Speed: 1.3mm/min Deflection: 0.5mm	2688	Mpa
Flexural strength	ASTM D790	Speed: 1.3mm/min Deflection: 5.0mm	76.84	Mpa
MFI	ASTM D1238	10.00 kg / 220 °C	5.07	g/10 min
Izod Impact	ISO 180	5.50J/notched/23°C	246.5	j/m ²
Filler Content	ISO3451/1	600°C/30 min	4.86	%
DSC	ISO 11357/6	10 °C/min N2 50ml/min	Click here	°c
Density	ISO 1183	23°C, 50% RH	1.07	gr/cm ³



- The uncertainty of the test result is based on confidence range of %95 and K=2 which is calculated and Announced due to the customers' demands.



Info@exirpolymer.com



+98 31 4564 3030



+98 912 962 3265



Exirpolymer.com



Fa.Exirpolymer.com



Ar.Exirpolymer.com