

Test results of PS SUB 1102

Description	Standard	Condition	Result	Unit
Tensile strength @Yield	ISO 527	Speed 5 mm/min Grip 115 mm	20.14	Mpa
Elongatin @ Break	ISO 527	Speed 5 mm/min Grip 115 mm	3.83	%
Tensile strength @ Break	ISO 527	Speed 5 mm/min Grip 115 mm	20.14	Mpa
Elongatin @ Yield	ISO 527	Speed 5 mm/min Grip 115 mm	3.83	%
Flexural Modulus	ASTM D790	Speed: 1.3mm/min Deflection: 0.5mm	2284	Mpa
Flexural strength	ASTM D790	Speed: 1.3mm/min Deflection: 5.0mm	36.00	Mpa
MFI	ASTM D1238	5.00 kg / 200 °C	9.4	g/10 min
Filler Content	ISO3451/1	600°C/30 min	19.38	%
DSC	ISO 11357/6	10 °C/min N2 50ml/min	Click here	°c
Density	ISO 1183	23°C, 50% RH	1.156	gr/cm ³



- The uncertainty of the test result is based on confidence range of %95 and K=2 which is calculated and Announced due to the customers' demands.

 Info@exirpolymer.com

 +98 31 4564 3030

 +98 912 962 3265

 Exirpolymer.com

 Fa.Exirpolymer.com

 Ar.Exirpolymer.com